



# EPDM

## Keltan®

### Keltan® 9650C

Amorphous ethylene-propylene rubber with high ENB (ethylidene norbornene) content and a high Mooney viscosity.

The very high Mw enables cost-efficient compounding, especially for dense profiles in building and domestic applications.

Typical application areas for this grade are dense profiles.

Property	Nominal Value	Unit	Test Method
Mooney Viscosity ML (1+8) 150 °C	60	MU	ISO 289
Ethylene content	51	wt. %	ASTM D 3900
ENB content	6.5	wt %	ASTM D 6047
Molecular weight distribution	Narrow		ARLANXEO